

COPY OF ALL CLAIMS

1. (canceled)
2. (currently amended) A process for preparing arrays of heterogeneous catalysts,
heterogeneous catalyst and/or their precursors, or combinations thereof,
comprising made up of a body having which has, preferably parallel, through-
channels and in which at least n through-channels comprise n different
heterogeneous catalysts, heterogeneous catalyst and/or their precursors, or
combinations thereof, where n is 2 or more, preferably 10, particularly preferably
100; comprising the following steps:
 - b1) preparing solutions, emulsions or and/or dispersions of elements or and/or
element compounds of the elements present in the catalysts, catalyst
precursors, or combinations thereof catalyst and/or catalyst precursor
and, optionally, if appropriate preparing dispersions of inorganic support
materials,
 - b2) optionally, if appropriate introducing adhesion promoters, binders,
viscosity regulators pH regulators or and/or solid inorganic supports into
the solutions, emulsions or and/or dispersions,
 - b3) simultaneously or successively coating catalyst supports present in the
channels of the body with the solutions, emulsions or and/or dispersions,
a predetermined amount of the solutions, emulsions or and/or dispersions
being introduced into each channel to obtain a predetermined composition
on the catalyst supports, to produce freshly impregnated moist channels,

- b4) treating and reacting with one or more reactive gases the freshly impregnated moist channels obtained after the coating, and
 - b5) optionally, if appropriate heating the body comprising the coated catalyst supports in the channels in the presence or absence of inert gases or reactive gases to a temperature in the range from 20 to 1500°C to dry, optionally with or without sintering or calcining, the catalysts, catalyst precursors, or combinations thereof catalysts and/or catalyst precursors.
3. (original) A process for preparing arrays of heterogeneous catalysts and/or their precursors made up of a body which has, preferably parallel, through-channels and in which at least n channels comprise n different heterogeneous catalysts and/or their precursors, where n is 2, preferably 10, particularly preferably 100, comprising the following steps:
- c1) preparing solutions, emulsions and/or dispersions of elements and/or element compounds of the chemical elements present in the catalyst and/or catalyst precursor and, if appropriate preparing dispersions of inorganic support materials,
 - c2) mixing predetermined amounts of the solutions, emulsions and/or dispersions with or without precipitation aids in one or more reaction vessels run in parallel,
 - c3) if appropriate introducing adhesion promoters, binders, viscosity regulators pH regulators and/or solid inorganic supports into the resultant mixture(s),

- c4) coating one or more predetermined channels of the body with the mixture or a plurality of mixtures,
 - c5) repeating steps c2) to c4) for other channels of the body until the channels containing the respective predetermined catalyst and/or catalyst precursor compositions are coated,
 - c6) treating and reacting with one or more reactive gases the freshly impregnated moist channels obtained after the coating, and
 - c7) if appropriate heating the coated body in the presence or absence of inert gases or reactive gases to a temperature in the range from 20 to 1500°C to dry, with or without sintering or calcining, the catalysts and/or catalyst precursors.
4. (original) A process for preparing arrays of heterogeneous catalysts and/or their precursors made up of a body which has, preferably parallel, through-channels and in which at least n channels comprise n different heterogeneous catalysts and/or their precursors, where n is 2, preferably 10, particularly preferably 100, comprising the following steps:
- d1) preparing solutions, emulsions and/or dispersions of elements and/or element compounds of the chemical elements present in the catalyst and/or catalyst precursor and, if appropriate preparing dispersions of inorganic support materials,
 - d2) mixing predetermined amounts of the solutions, emulsions and/or dispersions with or without precipitation aids in one or more reaction

vessels

run in parallel,

- d3) if appropriate introducing adhesion promoters, binders, viscosity regulators, pH regulators and/or solid inorganic supports into resultant mixture(s),
- d4) coating catalyst supports present in one or more predetermined channels of the body with the mixture or one or more of the mixtures,
- d5) repeating steps d2) to d4) for other channels of the body until the catalyst supports present in the channels of the body are coated with the respective predetermined catalyst compositions and/or catalyst precursor compositions,
- d6) treating and reacting with one or more reactive gases the freshly impregnated moist channels obtained after the coating, and
- d7) if appropriate heating the body comprising the coated catalyst supports in the channels in the presence or absence of inert gases or reactive gases to a temperature in the range from 20 to 1500°C to dry, with or without sintering or calcining, the catalysts and/or catalyst precursors.

5. (original) A process for preparing arrays of heterogeneous catalysts and/or their precursors made up of a body which has, preferably parallel, through-channels and in which at least n channels comprise n different heterogeneous catalysts and/or their precursors, where n is 2, preferably 10, particularly preferably 100, comprising the following steps:

- e1) reacting predetermined dry porous catalyst supports with one or more reactive gases for preparing predetermined supported catalysts outside or inside the body,
 - e2) if appropriate introducing the supported catalysts prepared outside the body into predetermined channels of the body, and
 - e3) if appropriate heating the filled body in the presence or absence of inert gases or reactive gases to a temperature in the range from 20 to 1500°C to dry, with or without sintering or calcining, the catalysts.
6. (original) A process for preparing arrays of heterogeneous catalysts and/or their precursors made up of a body which has, preferably parallel, through-channels and in which at least n channels comprise n different heterogeneous catalysts and/or their precursors, where n is 2, preferably 10, particularly preferably 100, comprising the following steps:
- f1) coating and if appropriate heating predetermined catalyst supports to prepare predetermined supported catalysts in the manner defined in claim 2 outside the body,
 - f2) introducing the supported catalysts into predetermined channels of the body,
 - f3) if appropriate heating the packed body in the presence or absence of inert gases or reactive gases to a temperature in the range from 20 to 1500°C to dry, with or without sintering or calcining, the catalysts.
7. (original) A process for preparing arrays of heterogeneous catalysts and/or their

precursors made up of a body which has, preferably parallel, through-channels and in which at least n channels comprise different heterogeneous catalysts and/or their precursors, where n is 2, preferably 10, particularly preferably 100, following steps:

- g1) simultaneous or sequential coating of the channels of the body with gasified chemical elements or their mixtures of the chemical elements present in the catalysts, and
- g2) if appropriate heating the coated body in the presence or absence of inert gases or reactive gases to a temperature in the range of from 20 to 1500°C to dry, with or without sintering or calcining, the catalysts and/or catalyst precursors.

8. (original) A process for preparing arrays of heterogeneous catalysts and/or their precursors made up of a body which has, preferably parallel, through-channels and in which at least n channels comprise n different heterogeneous catalysts and/or their precursors, where n is 2, preferably 10, particularly preferably 100, comprising the following steps:

- h1) simultaneous or sequential coating of the channels of the body with pulverulent chemical elements or their mixtures of the chemical elements present in the catalyst, and
- h2) if appropriate heating the coated body in the presence or absence of inert gases or reactive gases to a temperature in the range of from 20 to 1500°C to dry, and if appropriate sinter or calcine, the catalysts and/or

catalyst precursors.

9. (currently amended) An array obtainable by a process as claimed in claim 2 as ~~claimed in claim 1~~.
10. (original) A process for determining the activity, selectivity and/or long-term stability of the catalysts in an array as claimed in claim 9, comprising the following steps:
- i1) if appropriate activating the catalyst in the body,
 - i2) heating or cooling the body to a desired reaction temperature,
 - i3) passing a fluid reactant or fluid reaction mixture through channels of the body,
 - i4) discharge of the reacted fluids from individual or a plurality of collective channels of the body,
 - i5) analysis of the discharged reacted fluids,
 - i6) if appropriate comparative evaluation of the analytical results of a plurality of analyses.
11. (new) The process as claimed in claim 2, wherein n is at least 10.
12. (new) The process as claimed in claim 11, wherein n is at least 100.
13. (new) The process as claimed in claim 2, wherein the through-channels are parallel relative to each other.